

# PERFORMANCE TABLE

## Dek-Cap Flashing

ASTM METHOD	TEST DESCRIPTION	SPECIFICATION	TEST RESULTS
D412	Tensile Strength (min. psi rating)	1450 psi min.	1500 psi
D412	Ultimate Elongation (%)	350 min.	450
D1171	Resistance to Ozone-min. rating	100 (no cracks)	Passed
D573	Heat Aging - 70 hrs. at 100°C • Change in Hardness (points) • Change in Tensile Strength (%) • Change in Elongation (%)	± 15 max. ± 30 max. ± 50 max.	+3 +2 -3

ASTM METHOD	TEST DESCRIPTION	SPECIFICATION	TEST RESULTS
D2137	Low Temperature Brittleness- 3 mins. at -40°C	Non-brittle	Passed
D624	Tear Resistance Die C (min.) per inch of width min.	125 pounds per inch of width	Passed



Call our toll free number 800-387-9692 or visit [www.itwconstruction.ca](http://www.itwconstruction.ca) for general information.  
Visit ITW Buildex's web site [www.itwbuildex.com](http://www.itwbuildex.com) for the most current product and technical information.